

Resin Number: 29315

Last Updated: 5/28/2002

Material Number:

Page 1 of 1

DESCRIPTION

Varcum 29315 is a two-step, powdered phenolic resin.

APPLICATION

Special cold-press grinding wheel applications.

FEATURES

- Requires minimum amounts of wetting agents.
- Provides higher heat resistance.

TYPICAL PROPERTIES

		<u>Test Method</u>
Screen % on 200 Mesh	2.50	DCT 4007A
Inclined Plate Flow @ 125°C, mm	30.00	DCT 4009A
Hexa, %	14.05	DCT 4019A

Durez test methods are available upon request.

SOLUBILITY

Soluble in lower alcohols, ketones and esters, although solutions have slight haze or sediment. Not soluble in aromatic hydrocarbons, but solutions in true solvents will tolerate the addition of aromatic hydrocarbons.

STORAGE

This product is a stable material that has little or no tendency to lump when maintained in closed containers. Store in a cool, dry location at 75°F or less.

PACKAGING AND SHIPPING

Available in 50 pound bags. This product is not DOT regulated in bags.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING,
STORING OR USING THIS PRODUCT.