

Resin Number: 29335

Last Updated: 4/15/2003

Material Number:

Page 1 of 1

DESCRIPTION

Varcum 29335 is a high-condensation, two-step, powdered phenolic resin.

APPLICATION

Varcum 29335 is recommended for use in friction applications.

FEATURES

- Shorter flow results in reduced bond fluidity and permits faster cycle times.

TYPICAL PROPERTIES

		<u>Test Method</u>
Screen % on 200 Mesh	2.5 Max	DCT 4007A
Inclined Plate Flow @ 125°C, mm	15.00	DCT 4009B
Hexa, %	13.00	DCT 4019A

Durez test methods are available upon request.

SOLUBILITY

Soluble in lower alcohols, esters and ketones, although solutions have slight haze or sediment. Not soluble in aromatic hydrocarbons, but solutions in true solvents will tolerate the addition of aromatic hydrocarbons.

STORAGE

This product is a stable material that has little or no tendency to lump when maintained in closed containers. Store in a cool, dry location at 75°F or less.

PACKAGING AND SHIPPING

Available in non-returnable fiber drums, 225 pounds net. This product is not DOT regulated in drums.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING,
STORING OR USING THIS PRODUCT.