

Resin Number: 29109

Last Updated: 4/8/2004

Material Number:

Page 1 of 1

DESCRIPTION

Varcum 29109 is a thermosetting phenolic resin in lump form.

APPLICATION

Varcum 29109 is recommended for use in metal coating applications.

FEATURES

The use of modifying agents tend to reduce the maximum chemical resistance and, therefore, the incorporation of such agents is not generally recommended. Alcohol and/or ketone solvent systems are required with this product; the use of hydrocarbon solvents is not practical.

TYPICAL PROPERTIES

		<u>Test Method</u>
Softening point (B&R), °C	72.50	DCT 4000A
Cure @150°C, sec	65.00	DCT 4001A
G&H Viscosity	V	DCT 4003C

Durez test methods are available upon request.

STORAGE

Properties will change during storage. The degree of property change is dependent on the length and temperature of storage. For optimum property control, refrigeration at 40°F is necessary. Storage temperatures above 75°F must be avoided.

PACKAGING AND SHIPPING

Available in non-returnable fiber drums, 325 pounds net. Check with your sales representative for packaging options and availability.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING,
STORING OR USING THIS PRODUCT.