

Resin Number: 75202

Last Updated: 2/20/2001

Material Number:

Page 1 of 2

DESCRIPTION

Methylon 75202 is a metal coating resin produced by the reaction of a bisphenol epichlorohydrin type epoxy resin with a xylene-formaldehyde condensation polymer in a mixture of xylol, diacetone alcohol and butyl cellosolve.

APPLICATION

Methylon 75202 should be used where color and flexibility are important as in appliance primers.

USES

- Linings for drums, cans and pails.
- Finishes for appliances.
- Industrial coating requiring light color, chemical resistance and flexibility.
- Primers needing chemical resistance properties.

FEATURES

- Light color and excellent flexibility.
- Outstanding resistance to chemicals, solvents, acids, alkalis, and soap solutions.
- Compatible with epoxies, polyvinyl butyral, short and medium oil alkyds, urea and melamine formaldehyde resins.
- Cured films have excellent adhesion, heat resistance and mar-resistance.

TYPICAL PROPERTIES

		<u>Test Method</u>
G&H Viscosity	Z3	DCT 4003A
NV (135°C, 2.5g, 45 min), %	65.00	DCT 4005D
Color	13	DCT 4075A
Specific Gravity	1.02	DCT 5075

Durez test methods are available upon request.

SOLUBILITY

Soluble in polar solvents such as diacetone alcohol, MEK, MIBK, butyl alcohol or mixtures of these solvents with aromatic hydrocarbon solvents.

STORAGE

This product, if stored at room temperature, will slowly change in properties. To maintain properties, the product should be kept in a cool (less than 50°F), dry location in closed containers.

PACKAGING AND SHIPPING

Available in 55 gallon steel drums, 450 pounds net. This product is DOT regulated and shipped as a FLAMMABLE LIQUID, UN 1866.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING,
STORING OR USING THIS PRODUCT.

Durez

DUREZ CORPORATION

14131 Midway Rd., Ste. 500 Addison, Texas 75001

972/763-2800

IMPORTANT! The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guaranty, express or implied is made regarding performance stability or otherwise. This information is not intended to be all inclusive as the manner and conditions of use, handling, storage and other factors may involve other and additional safety and performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe safe handling and use remains the responsibility of the customer. No suggestions for use are intended as and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State or local laws.