

Resin Number: 94917
Material Number:

Last Updated: 3/12/2001
Page 1 of 1

DESCRIPTION

Varcum 94917 is a heat reactive one-step phenolic resin in a solution of butyl alcohol.

APPLICATION

Varcum 94917 is designed for use in metal coating formulations.

TYPICAL PROPERTIES

		<u>Test Method</u>
Viscosity @ 25°C, cps	14,000.00	DCT 4003F
Non Volatile, %	74.00	DCT 4005A
Xylene Tolerance, %	800 % Min	DCT 4012
Color	10 Max	DCT 4075A
Color	10 Max	DCT 4075A

Durez test methods are available upon request.

SOLUBILITY

Dilutable in esters, ketones, higher alcohols, and aromatic hydrocarbon-alcohol mixtures. Limited solubility in lower alcohols. Will tolerate the addition of some aromatic hydrocarbons.

STORAGE

This product is a heat reactive material and should be stored in closed containers at, or below 40°F.

PACKAGING AND SHIPPING

Available in 55 gallon steel drums, 475 pounds net. This product is DOT regulated and shipped as a FLAMMABLE LIQUID, UN1866.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING,
STORING OR USING THIS PRODUCT.